

# LG ABS LG704W

LG Chem Ltd. - Acrylonitrile Butadiene Styrene

Friday, May 24, 2019

## General Information

### Product Description

#### Description

- Low Gloss, Heat Resistance

#### Application

- Automotive Interior housing (Room Mirror Housing, Console Box Etc.)

### General

Material Status	• Commercial: Active		
Availability	• Asia Pacific • Europe	• Latin America • North America	
Features	• Good Heat Resistance	• Low Gloss	
Uses	• Automotive Applications	• Automotive Interior Parts	• Housings
Processing Method	• Injection Molding		

## ASTM & ISO Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity <sup>2</sup>	1.04	g/cm <sup>3</sup>	ASTM D792
Density (23°C)	1.05	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	7.0	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	7.0	g/10 min	ISO 1133
Molding Shrinkage - Flow (23°C, 3.20 mm, Injection Molded)	0.40 to 0.70	%	ASTM D955
Molding Shrinkage - Flow <sup>3</sup> (23°C, 3.20 mm)	0.40 to 0.70	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus <sup>4</sup> (23°C, 3.20 mm, Injection Molded)	2450	MPa	ASTM D638
Tensile Modulus (23°C, 4.00 mm, Injection Molded)	2400	MPa	ISO 527-2/50
Tensile Strength <sup>4</sup>			ASTM D638
Yield, 23°C, 3.20 mm, Injection Molded	53.0	MPa	
Tensile Stress			ISO 527-2/50
Yield, 23°C, 4.00 mm, Injection Molded	53.0	MPa	
Tensile Elongation <sup>4</sup>			ASTM D638
Break, 23°C, 3.20 mm, Injection Molded	> 10	%	
Tensile Strain			ISO 527-2/50
Break, 23°C, 4.00 mm, Injection Molded	> 10	%	
Flexural Modulus <sup>5</sup> (23°C, 3.20 mm, Injection Molded)	2600	MPa	ASTM D790
Flexural Modulus <sup>6</sup> (23°C, 4.00 mm, Injection Molded)	2500	MPa	ISO 178
Flexural Strength <sup>5</sup> (23°C, 3.20 mm, Injection Molded)	84.3	MPa	ASTM D790
Flexural Stress <sup>6</sup> (23°C, 4.00 mm, Injection Molded)	83.0	MPa	ISO 178

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

# LG ABS LG704W

## LG Chem Ltd. - Acrylonitrile Butadiene Styrene

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength <sup>7</sup>			ISO 179/1eA
-30°C, Injection Molded	6.0	kJ/m <sup>2</sup>	
23°C, Injection Molded	14	kJ/m <sup>2</sup>	
Notched Izod Impact			ASTM D256
-30°C, 3.20 mm, Injection Molded	60	J/m	
-30°C, 6.40 mm, Injection Molded	50	J/m	
23°C, 3.20 mm, Injection Molded	170	J/m	
23°C, 6.40 mm, Injection Molded	160	J/m	
Notched Izod Impact Strength <sup>7</sup>			ISO 180/1A
-30°C, Injection Molded	6.0	kJ/m <sup>2</sup>	
23°C, Injection Molded	15	kJ/m <sup>2</sup>	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C, Injection Molded)	111		ASTM D785
Rockwell Hardness (R-Scale)	111		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed, 6.40 mm, Injection Molded	97.0	°C	
Heat Deflection Temperature <sup>3</sup>			ISO 75-2/Af
1.8 MPa, Unannealed, 4.00 mm	90.0	°C	
Vicat Softening Temperature	106	°C	ASTM D1525 <sup>8</sup>
Vicat Softening Temperature	108	°C	ISO 306/B50

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature	80 to 90	°C
Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	0.070	%
Rear Temperature	180 to 200	°C
Middle Temperature	200 to 220	°C
Front Temperature	220 to 230	°C
Nozzle Temperature	220 to 230	°C
Processing (Melt) Temp	220 to 250	°C
Mold Temperature	40 to 60	°C
Back Pressure <sup>9</sup>	0.981 to 2.94	MPa

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 23°C

<sup>3</sup> Injection Molded

<sup>4</sup> 50 mm/min

<sup>5</sup> 15 mm/min

<sup>6</sup> 2.0 mm/min

<sup>7</sup> 4mm

<sup>8</sup> Rate A (50°C/h), Loading 2 (50 N)

<sup>9</sup> Hydraulic Type