



Lupoy® GN5001RFM

LG Chem Ltd. - Polycarbonate + ABS

Friday, May 24, 2019

General Information

Product Description

Description
Halogen Free Flame Retardant, General Purpose

Application
E&E(Housing)

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Latin America	
	• Europe	• North America	
Features	• Flame Retardant	• General Purpose	• Halogen Free
Uses	• Electrical/Electronic Applications		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.18	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	9.5	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.40 to 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield, 3.20 mm)	54.9	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	> 50	%	ASTM D638
Flexural Modulus ³ (6.40 mm)	2350	MPa	ASTM D790
Flexural Strength ³ (Yield, 6.40 mm)	86.3	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	490	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load ⁴ 0.45 MPa, Unannealed, 6.40 mm	92.0	°C	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.6 mm)	V-0		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	60 to 80	°C
Drying Time	4.0 to 6.0	hr
Suggested Max Moisture	< 0.020	%
Rear Temperature	225 to 255	°C
Middle Temperature	230 to 260	°C
Front Temperature	230 to 260	°C
Nozzle Temperature	230 to 250	°C
Processing (Melt) Temp	230 to 260	°C
Mold Temperature	50 to 70	°C

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Lupoy® GN5001RFM

LG Chem Ltd. - Polycarbonate + ABS

Injection	Nominal Value	Unit
Screw Speed	40 to 70	rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

² 50 mm/min

³ 10 mm/min

⁴ 4.6kg