

General Information
Product Description

Description

General Purpose, High Stiffness, Halogen Free Flame Retardent

Application

IT/OA(Notebook PC Housing)

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • Latin America • North America
Filler / Reinforcement	• Mineral, 15% Filler by Weight
Features	• Flame Retardant • General Purpose • Halogen Free • High Stiffness
Uses	• Electrical Housing • Electrical/Electronic Applications
Processing Method	• Injection Molding

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.27	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	11	g/10 min	ASTM D1238
Molding Shrinkage - Flow (23°C, 3.20 mm, Injection Molded)	0.20 to 0.40	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ²			ASTM D638
Yield, 23°C, 3.20 mm, Injection Molded	66.7	MPa	
Tensile Elongation ²			ASTM D638
Break, 23°C, 3.20 mm, Injection Molded	20	%	
Flexural Modulus ³ (23°C, 3.20 mm, Injection Molded)	4410	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm, Injection Molded)	59	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 6.40 mm, Injection Molded	95.0	°C	
RTI Elec	60.0	°C	UL 746
RTI Imp	60.0	°C	UL 746
RTI Str	60.0	°C	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.0 mm)	V-0		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	75 to 85	°C
Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	0.020	%

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Lupoy® GN5151RFA

LG Chem Ltd. - Polycarbonate + ABS

Injection	Nominal Value	Unit
Rear Temperature	230 to 250	°C
Middle Temperature	245 to 265	°C
Front Temperature	260 to 275	°C
Nozzle Temperature	260 to 275	°C
Processing (Melt) Temp	245 to 275	°C
Mold Temperature	60 to 80	°C
Back Pressure	0.981 to 1.96	MPa
Screw Speed	40 to 70	rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

² 50 mm/min

³ 10 mm/min