

**General Information**
**Product Description**

Description

General Purpose, Transparency

Application

IT/OA, E&amp;E Housing and Components

Automotive Exterior and Interior

**General**

Material Status	• Commercial: Active		
Availability	• Asia Pacific • Europe	• Latin America • North America	
Features	• General Purpose		
Uses	• Automotive Applications • Automotive Exterior Parts	• Automotive Interior Parts • Electrical Housing	• Electrical/Electronic Applications • General Purpose
Appearance	• Clear/Transparent		
Processing Method	• Injection Molding		

**ASTM & ISO Properties<sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.20	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	11	g/10 min	ASTM D1238
Molding Shrinkage - Flow (23°C, 3.20 mm, Injection Molded)	0.50 to 0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>2</sup>			ASTM D638
Yield, 23°C, 3.20 mm, Injection Molded	61.8	MPa	
Tensile Elongation <sup>2</sup>			ASTM D638
Break, 23°C, 3.20 mm, Injection Molded	150	%	
Flexural Modulus <sup>3</sup> (23°C, 3.20 mm, Injection Molded)	2260	MPa	ASTM D790
Flexural Strength <sup>3</sup> (23°C, 3.20 mm, Injection Molded)	98.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm, Injection Molded)	740	J/m	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C, Injection Molded)	118		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed, 6.40 mm, Injection Molded	130	°C	
Vicat Softening Temperature	141	°C	ASTM D1525 <sup>4</sup>
RTI Elec	130	°C	UL 746
RTI Imp	130	°C	UL 746
RTI Str	130	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (23°C)	2.0E+17	ohms-cm	ASTM D257
Dielectric Strength (23°C, 1.00 mm)	17	kV/mm	ASTM D149

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

# Lupoy® GP1000M

## LG Chem Ltd. - Polycarbonate

Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	250	V	IEC 60112

  

Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.5 mm		HB	
3.2 mm		HB	

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature	100 to 120	°C
Drying Time	3.0 to 5.0	hr
Suggested Max Moisture	0.020	%
Rear Temperature	260 to 280	°C
Middle Temperature	280 to 300	°C
Front Temperature	300 to 320	°C
Nozzle Temperature	300 to 320	°C
Processing (Melt) Temp	300 to 320	°C
Mold Temperature	80 to 120	°C
Back Pressure	0.981 to 3.92	MPa
Screw Speed	40 to 70	rpm

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 50 mm/min

<sup>3</sup> 10 mm/min

<sup>4</sup> Rate A (50°C/h), Loading 2 (50 N)