

**General Information**
**Product Description**

## Description

General Purpose, High Impact, Good Coloring, Chemical Resistance

## Application

Mobile Phone Housing

**General**

Material Status	• Commercial: Active		
Availability	• Asia Pacific • Europe	• Latin America • North America	
Features	• Chemical Resistant • General Purpose	• Good Colorability • High Impact Resistance	
Uses	• Cell Phones	• Electrical Housing	• Electrical/Electronic Applications
Processing Method	• Injection Molding		

**ASTM & ISO Properties <sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.20	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	11	g/10 min	ASTM D1238
Molding Shrinkage - Flow (23°C, 3.20 mm, Injection Molded)	0.50 to 0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>2</sup>			ASTM D638
Yield, 23°C, 3.20 mm, Injection Molded	54.9	MPa	
Tensile Elongation <sup>2</sup>			ASTM D638
Break, 23°C, 3.20 mm, Injection Molded	100	%	
Flexural Modulus <sup>3</sup> (23°C, 3.20 mm, Injection Molded)	2160	MPa	ASTM D790
Flexural Strength <sup>3</sup> (23°C, 3.20 mm, Injection Molded)	88.3	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C, 3.20 mm, Injection Molded	290	J/m	
23°C, 3.20 mm, Injection Molded	690	J/m	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C, Injection Molded)	117		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed, 6.40 mm, Injection Molded	128	°C	
RTI Elec	80.0	°C	UL 746
RTI Imp	80.0	°C	UL 746
RTI Str	80.0	°C	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.70 mm)	HB		UL 94

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

# Lupoy® SC1004ML

## LG Chem Ltd. - Polycarbonate

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature	100 to 110	°C
Drying Time	3.0 to 5.0	hr
Suggested Max Moisture	0.020	%
Rear Temperature	275 to 290	°C
Middle Temperature	285 to 305	°C
Front Temperature	290 to 310	°C
Nozzle Temperature	285 to 305	°C
Processing (Melt) Temp	290 to 310	°C
Mold Temperature	80 to 110	°C
Back Pressure	0.981 to 3.92	MPa
Screw Speed	40 to 70	rpm

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 50 mm/min

<sup>3</sup> 10 mm/min