

LG ABS XR401

LG Chem Ltd. - Acrylonitrile Butadiene Styrene

Saturday, July 20, 2019

General Information

Product Description

Description

- Heat Resistance

Applications

- Electric & Electronic Housing (Frame etc),
- Automotives Interior & Exterior Housing (lamp housing etc)

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific • Europe	• Latin America • North America	
Features	• Good Heat Resistance		
Uses	• Automotive Exterior Parts	• Automotive Interior Parts	• Electrical Housing
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity ²	1.05	g/cm ³	ASTM D792
Density (23°C)	1.05	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	9.0	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	9.00	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (23°C, 3.20 mm, Injection Molded)	0.40 to 0.70	%	ASTM D955
Molding Shrinkage - Flow ³ (23°C, 3.20 mm)	0.40 to 0.70	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ⁴ (23°C, 3.20 mm, Injection Molded)	2400	MPa	ASTM D638
Tensile Modulus (23°C, 4.00 mm, Injection Molded)	2300	MPa	ISO 527-2/50
Tensile Strength ⁴			ASTM D638
Yield, 23°C, 3.20 mm, Injection Molded	49.0	MPa	
Tensile Stress			ISO 527-2/50
Yield, 23°C, 4.00 mm, Injection Molded	49.0	MPa	
Tensile Strain			ISO 527-2/50
Yield, 23°C, 4.00 mm, Injection Molded	> 5.0	%	
Tensile Elongation ⁴			ASTM D638
Break, 23°C, 3.20 mm, Injection Molded	> 15	%	
Tensile Strain			ISO 527-2/50
Break, 23°C, 4.00 mm, Injection Molded	> 15	%	
Flexural Modulus ⁵ (23°C, 3.20 mm, Injection Molded)	2550	MPa	ASTM D790
Flexural Modulus ⁶ (23°C, 4.00 mm, Injection Molded)	2350	MPa	ISO 178
Flexural Strength ⁵ (23°C, 3.20 mm, Injection Molded)	79.0	MPa	ASTM D790
Flexural Stress ⁶ (23°C, 4.00 mm, Injection Molded)	75.0	MPa	ISO 178

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

LG ABS XR401

LG Chem Ltd. - Acrylonitrile Butadiene Styrene

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁷			ISO 179/1eA
-30°C, Injection Molded	9.0	kJ/m ²	
23°C, Injection Molded	23	kJ/m ²	
Notched Izod Impact			ASTM D256
-30°C, 3.20 mm, Injection Molded	90	J/m	
-30°C, 6.40 mm, Injection Molded	80	J/m	
23°C, 3.20 mm, Injection Molded	270	J/m	
23°C, 6.40 mm, Injection Molded	250	J/m	
Notched Izod Impact Strength ⁷			ISO 180/1A
-30°C, Injection Molded	8.0	kJ/m ²	
23°C, Injection Molded	23	kJ/m ²	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C, Injection Molded)	110		ASTM D785
Rockwell Hardness (R-Scale)	112		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load ⁸			ASTM D648
1.8 MPa, Unannealed, 6.40 mm, Injection Molded	97.0	°C	
Heat Deflection Temperature ⁹			ISO 75-2/Af
1.8 MPa, Unannealed, 4.00 mm	88.0	°C	
Vicat Softening Temperature	106	°C	ASTM D1525 ¹⁰
Vicat Softening Temperature	106	°C	ISO 306/B50
CLTE - Flow (23 to 60°C)	8.0E-5 to 9.0E-5	cm/cm/°C	ISO 11359-2
CLTE - Transverse (23 to 60°C)	8.0E-5 to 9.0E-5	cm/cm/°C	ISO 11359-2
RTI Elec	60.0	°C	UL 746
RTI Imp	60.0	°C	UL 746
RTI Str	60.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (23°C)	1.5E+3	ohms-cm	ASTM D257
Dielectric Strength (23°C, 1.00 mm)	33	kV/mm	ASTM D149
Arc Resistance	PLC 6		ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.5 mm	HB		
3.0 mm	HB		

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	80 to 90	°C
Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	0.050	%
Rear Temperature	180 to 210	°C
Middle Temperature	210 to 230	°C
Front Temperature	230 to 240	°C
Nozzle Temperature	230 to 240	°C
Processing (Melt) Temp	230 to 260	°C
Mold Temperature	40 to 60	°C
Back Pressure ¹¹	0.981 to 2.94	MPa

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

LG ABS XR401

LG Chem Ltd. - Acrylonitrile Butadiene Styrene

Notes

¹ Typical properties: these are not to be construed as specifications.

² 23°C

³ Injection molded

⁴ 50 mm/min

⁵ 15 mm/min

⁶ 2.0 mm/min

⁷ 4mm

⁸ Edgewise

⁹ Injection Molded

¹⁰ Rate A (50°C/h), Loading 2 (50 N)

¹¹ Hydraulic Type