

ForTii® H11

DSM Engineering Plastics - Polyphthalamide

Tuesday, January 21, 2020

General Information

Product Description

30% Glass Reinforced, PA4T, High Flow, Halogen free and free of red phosphorous

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Additive	• Flame Retardant		
Features	• Flame Retardant • Halogen Free	• High Flow • Low (to None) Phosphorus Content	
Processing Method	• Injection Molding		
Resin ID (ISO 1043)	• PPA-GF30 FR(40)		

ASTM & ISO Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density	1.46	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	1.1	--	%	
Flow	0.30	--	%	
Water Absorption				ISO 62
Equilibrium, 23°C, 50% RH	1.8	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	11000	11000	MPa	ISO 527-2
Tensile Stress (Break)	140	135	MPa	ISO 527-2
Tensile Strain (Break)	1.9	1.8	%	ISO 527-2
Flexural Modulus	10500	10500	MPa	ISO 178
Flexural Stress	210	200	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
23°C	8.0	8.0	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
23°C	40	40	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				ISO 75-2/A
1.8 MPa, Unannealed	295	--	°C	
Melting Temperature ²	325	--	°C	ISO 11357-3
CLTE - Flow	3.0E-5	--	cm/cm/°C	ASTM D696
CLTE - Flow	2.1E-5	--	cm/cm/°C	ISO 11359-2
CLTE - Transverse	5.0E-5	--	cm/cm/°C	ASTM D696
CLTE - Transverse	6.5E-5	--	cm/cm/°C	ISO 11359-2
RTI Elec (0.35 mm)	140	--	°C	UL 746

UL and the UL logo are trademarks of UL LLC © 2020. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

ForTii® H11

DSM Engineering Plastics - Polyphthalamide

Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	> 1.0E+15	1.0E+15	ohms-cm	IEC 60093
Relative Permittivity				IEC 60250
100 Hz	4.40	5.30		
1 MHz	4.10	4.30		
1.00 GHz	3.90	--		
Comparative Tracking Index	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification				IEC 60695-11-10, -20
0.40 mm	V-0	--		
1.5 mm	V-0	--		

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min