

General Information
General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity (Natural)	1.17	g/cm ³	ASTM D792
Density (Natural)	1.17	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	22	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	22	g/10 min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.30	%	ASTM D955
Molding Shrinkage - Across Flow (3.20 mm)	0.30	%	ASTM D955
Molding Shrinkage			ISO 294-4
Across Flow : 2.00 mm	0.30	%	
Flow : 2.00 mm	0.30	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ²	2500	MPa	ASTM D638
Tensile Modulus	2500	MPa	ISO 527-2/50
Tensile Strength ² (Yield)	55.0	MPa	ASTM D638
Tensile Stress (Yield)	55.0	MPa	ISO 527-2/50
Tensile Strength ² (Break)	34.0	MPa	ASTM D638
Tensile Stress (Break)	45.0	MPa	ISO 527-2/50
Tensile Elongation ² (Break)	25	%	ASTM D638
Tensile Strain (Break)	10	%	ISO 527-2/50
Flexural Modulus ³	2400	MPa	ASTM D790
Flexural Modulus ⁴	2500	MPa	ISO 178
Flexural Strength ³	79.0	MPa	ASTM D790
Flexural Stress ⁴	90.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁵ (23°C)	2.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength ⁵ (23°C)	30	kJ/m ²	ISO 179/1eU
Notched Izod Impact			ASTM D256
23°C, 3.18 mm	20	J/m	
23°C, 6.35 mm	20	J/m	
Notched Izod Impact Strength ⁵ (23°C)	2.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			ASTM D256
-5°C, 3.18 mm	260	J/m	
-5°C, 6.35 mm	250	J/m	
Unnotched Izod Impact Strength ⁵ (23°C)	25	kJ/m ²	ISO 180/1U
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	117		ASTM D785

UL and the UL logo are trademarks of UL LLC © 2020. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Starex LD-0955

LOTTE ADVANCED MATERIALS CO., LTD. - Polymethyl Methacrylate Acrylic

Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	117		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 0.45 MPa, Unannealed, 6.40 mm	99.0	°C	ASTM D648
Heat Deflection Temperature 0.45 MPa, Unannealed, 4.00 mm	80.0	°C	ISO 75-2/B
Deflection Temperature Under Load 1.8 MPa, Unannealed, 6.40 mm	79.0	°C	ASTM D648
Heat Deflection Temperature 1.8 MPa, Unannealed, 4.00 mm	75.0	°C	ISO 75-2/A
Vicat Softening Temperature	97.0	°C	ISO 306/B50

Processing Information

Injection	Nominal Value	Unit
Drying Temperature		
Desiccant Dryer	90	°C
Hot Air Dryer	90	°C
Drying Time		
Desiccant Dryer	2.0 to 4.0	hr
Hot Air Dryer	4.0	hr
Suggested Max Moisture	0.050	%
Rear Temperature	220 to 230	°C
Middle Temperature	230 to 240	°C
Front Temperature	240 to 250	°C
Nozzle Temperature	250	°C
Mold Temperature	50 to 80	°C
Injection Pressure	98.1	MPa
Back Pressure	0.490 to 2.45	MPa
Screw Speed	50 to 80	rpm

Injection Notes

Hot Runner Temperature: 230 to 250°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 5.0 mm/min

³ 2.8 mm/min

⁴ 2.0 mm/min

⁵ 4mm