



Braskem PP TI4900M

Braskem America Inc. - Polypropylene Impact Copolymer

Friday, September 20, 2019

General Information

Product Description

Very high flexural modulus, high melt flow

Applications

Suggested uses include compounding, automotive interior trim, intricately designed parts, thin-walled parts

General

Material Status	• Commercial: Active
Availability	• North America
Features	• High Flow • High Stiffness
Uses	• Automotive Applications • Compounding • Automotive Interior Trim • Thin-walled Packaging
Agency Ratings	• FDA 21 CFR 177.1520

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	115	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield)	29.6	MPa	ASTM D638
Tensile Elongation ² (Yield)	5.0	%	ASTM D638
Flexural Modulus - 1% Secant ³	1450	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	37	J/m	ASTM D256A
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	85		ASTM D785

Notes

¹ Typical properties: these are not to be construed as specifications.

² 51 mm/min

³ 1.3 mm/min