

ACRYLITE® M30

Röhm GmbH - Polymethyl Methacrylate Acrylic

Tuesday, January 21, 2020

General Information

Product Description

ACRYLITE® M30 acrylic polymer is an amorphous thermoplastic molding compound based on polymethyl methacrylate (PMMA).

Typical properties of ACRYLITE® acrylic polymers are:

- excellent weather resistance
- high light transmission
- high mechanical strength
- high surface hardness and mar resistance
- good melt flow rate
- versatile colorability due to crystal clarity

The special properties of ACRYLITE M30 polymer are:

- medium heat resistance
- high melt flow rate
- UV light transmitting
- medium levels of lubricant

Application:

Used for injection molding optical and technical parts.

General

Material Status	• Commercial: Active
Availability	• North America
Additive	• Lubricant
Features	<ul style="list-style-type: none"> • Amorphous • Good Colorability • Good Weather Resistance • High Clarity • High Flow • High Hardness • High Light Transmission • High Scratch Resistance • High Strength • Lubricated • Medium Heat Resistance
Uses	<ul style="list-style-type: none"> • Displays • Lenses • Lighting Applications • Medical/Healthcare Applications
Agency Ratings	• EC 1907/2006 (REACH)
Appearance	• Clear/Transparent
Forms	• Pellets
Processing Method	• Injection Molding

ASTM & ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.19	g/cm ³	ASTM D792
Apparent (Bulk) Density	0.66	g/cm ³	ASTM D1895
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	24	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.30 to 0.60	%	ASTM D955
Water Absorption (Equilibrium)	< 0.30	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3240	MPa	ASTM D638
Tensile Strength	63.4	MPa	ASTM D638
Tensile Elongation (Yield)	2.0 to 4.0	%	ASTM D638

UL and the UL logo are trademarks of UL LLC © 2020. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

ACRYLITE® M30

Röhm GmbH - Polymethyl Methacrylate Acrylic

Mechanical	Nominal Value	Unit	Test Method
Tensile Elongation (Break)	2.0 to 4.0	%	ASTM D638
Flexural Modulus	3170	MPa	ASTM D790
Flexural Strength	107	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 6.35 mm)	19	J/m	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	89		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 1.8 MPa, Annealed, 6.35 mm	82.2	°C	ASTM D648
Vicat Softening Temperature	90.0	°C	ASTM D1525
CLTE - Flow (0 to 100°C)	7.2E-5	cm/cm/°C	ASTM D696
Optical	Nominal Value	Unit	Test Method
Transmittance (3200 µm)	92.0	%	ASTM D1003
Haze (3200 µm)	< 1.00	%	ASTM D1003
Yellowness Index (3.20 mm)	< 1.0	YI	ASTM D1925

Notes

¹ Typical properties: these are not to be construed as specifications.