

ForTii® MX3

DSM Engineering Plastics - Polyphthalamide

Tuesday, January 21, 2020

General Information

Product Description

50% Glass Reinforced, PA4T, Heat Stabilized, for Automotive applications

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 50% Filler by Weight		
Additive	• Heat Stabilizer		
Features	• Heat Stabilized		
Uses	• Automotive Applications		
Processing Method	• Injection Molding		
Resin ID (ISO 1043)	• PPA-GF50		

ASTM & ISO Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density	1.65	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	0.90	--	%	
Flow	0.35	--	%	
Water Absorption				ISO 62
Equilibrium, 23°C, 50% RH	1.4	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus				ISO 527-2
--	18000	18000	MPa	
-40°C	18000	--	MPa	
40°C	17700	--	MPa	
80°C	16800	--	MPa	
100°C	15700	--	MPa	
120°C	12400	--	MPa	
150°C	8200	--	MPa	
160°C	7700	--	MPa	
180°C	7100	--	MPa	
200°C	6800	--	MPa	

UL and the UL logo are trademarks of UL LLC © 2020. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

ForTii® MX3

DSM Engineering Plastics - Polyphthalamide

Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Stress				ISO 527-2
Break	260	250	MPa	
Break, -40°C	280	--	MPa	
Break, 40°C	250	--	MPa	
Break, 80°C	220	--	MPa	
Break, 100°C	195	--	MPa	
Break, 120°C	155	--	MPa	
Break, 150°C	115	--	MPa	
Break, 160°C	105	--	MPa	
Break, 180°C	90.0	--	MPa	
Break, 200°C	82.0	--	MPa	
Tensile Strain				ISO 527-2
Break	2.0	2.0	%	
Break, -40°C	2.0	--	%	
Break, 40°C	2.1	--	%	
Break, 80°C	2.3	--	%	
Break, 100°C	2.6	--	%	
Break, 120°C	3.6	--	%	
Break, 150°C	5.7	--	%	
Break, 160°C	6.0	--	%	
Break, 180°C	6.0	--	%	
Break, 200°C	6.0	--	%	
Flexural Modulus				ISO 178
--	18000	--	MPa	
120°C	11700	--	MPa	
160°C	7500	--	MPa	
Flexural Stress	400	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	12	11	kJ/m ²	
23°C	12	11	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	75	65	kJ/m ²	
23°C	90	80	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				ISO 75-2/A
1.8 MPa, Unannealed	305	--	°C	
Melting Temperature ²	325	--	°C	ISO 11357-3
CLTE - Flow	2.7E-5	--	cm/cm/°C	ASTM D696
CLTE - Transverse	3.0E-5	--	cm/cm/°C	ASTM D696
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	> 1.0E+15	> 1.0E+15	ohms-cm	IEC 60093
Relative Permittivity				IEC 60250
100 Hz	5.10	5.80		
1 MHz	4.80	5.00		

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min