

LG ABS SH610A

LG Chem Ltd. - Acrylonitrile Butadiene Styrene

Saturday, July 20, 2019

General Information

Product Description

Description

- General Purpose, High Impact

Application

- Bag, Automobile Interior

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • Latin America • North America
Features	• General Purpose • High Impact Resistance
Uses	• Automotive Interior Parts • Bags
RoHS Compliance	• RoHS Compliant
Processing Method	• Extrusion

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity ²	1.04	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	5.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (23°C, 3.20 mm, Injection Molded)	0.40 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ³ (23°C, 3.20 mm, Injection Molded)	1880	MPa	ASTM D638
Tensile Strength ³			ASTM D638
Yield, 23°C, 3.20 mm, Injection Molded	41.0	MPa	
Tensile Elongation ³			ASTM D638
Yield, 23°C, 3.20 mm, Injection Molded	> 5.0	%	
Tensile Elongation ³			ASTM D638
Break, 23°C, 3.20 mm, Injection Molded	> 15	%	
Flexural Modulus ⁴ (23°C, 3.20 mm, Injection Molded)	2050	MPa	ASTM D790
Flexural Strength ⁴ (23°C, 3.20 mm, Injection Molded)	63.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C, 3.20 mm, Injection Molded	210	J/m	
-30°C, 6.40 mm, Injection Molded	190	J/m	
23°C, 3.20 mm, Injection Molded	490	J/m	
23°C, 6.40 mm, Injection Molded	420	J/m	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C, Injection Molded)	97		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load ⁵			ASTM D648
1.8 MPa, Unannealed, 6.40 mm, Injection Molded	87.0	°C	
Vicat Softening Temperature	94.0	°C	ASTM D1525 ⁶

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

LG ABS SH610A

LG Chem Ltd. - Acrylonitrile Butadiene Styrene

Thermal	Nominal Value	Unit	Test Method
RTI Elec	60.0	°C	UL 746
RTI Imp	60.0	°C	UL 746
RTI Str	60.0	°C	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.5 mm)	HB		UL 94

Processing Information

Extrusion	Nominal Value	Unit
Drying Temperature	70 to 80	°C
Drying Time	3.0 to 4.0	hr
Cylinder Zone 1 Temp.	180 to 210	°C
Cylinder Zone 2 Temp.	190 to 230	°C
Cylinder Zone 3 Temp.	200 to 250	°C
Cylinder Zone 4 Temp.	200 to 250	°C
Adapter Temperature	200 to 250	°C
Melt Temperature	200 to 250	°C
Die Temperature	200 to 250	°C

Extrusion Notes

Minimum Moisture Content: 0.01%

Roll Stack Temperature, Top: 70 to 100°C

Roll Stack Temperature, Middle: 70 to 90°C

Roll Stack Temperature, Bottom: 60 to 90°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 23°C

³ 50 mm/min

⁴ 15 mm/min

⁵ Edgewise

⁶ Rate A (50°C/h), Loading 2 (50 N)