

LG ASA LI912

LG Chem Ltd. - Acrylonitrile Styrene Acrylate

Saturday, July 20, 2019

General Information

Product Description

Description

- Good Weatherability, General Purpose

Application

- Mail Box, Sprinkler, Sash Joiner, Toy, Satellite Antenna Cover

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific • Europe	• Latin America • North America	
Features	• General Purpose	• Weather Resistant	
Uses	• Outdoor Applications	• Toys	
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity ²	1.07	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	12	g/10 min	ASTM D1238
Molding Shrinkage - Flow (23°C, 3.20 mm, Injection Molded)	0.40 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ³ (23°C, 3.20 mm, Injection Molded)	2160	MPa	ASTM D638
Tensile Strength ³			ASTM D638
Yield, 23°C, 3.20 mm, Injection Molded	49.0	MPa	
Tensile Elongation ³			ASTM D638
Break, 23°C, 3.20 mm, Injection Molded	25	%	
Flexural Modulus ⁴ (23°C, 3.20 mm, Injection Molded)	2300	MPa	ASTM D790
Flexural Strength ⁴ (23°C, 3.20 mm, Injection Molded)	79.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C, 3.20 mm, Injection Molded	40	J/m	
-30°C, 6.40 mm, Injection Molded	40	J/m	
23°C, 3.20 mm, Injection Molded	180	J/m	
23°C, 6.40 mm, Injection Molded	160	J/m	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C, Injection Molded)	103		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load ⁵			ASTM D648
1.8 MPa, Unannealed, 6.40 mm, Injection Molded	86.0	°C	
Vicat Softening Temperature	95.0	°C	ASTM D1525 ⁶
RTI Elec	50.0	°C	UL 746
RTI Imp	50.0	°C	UL 746
RTI Str	50.0	°C	UL 746

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

LG ASA LI912

LG Chem Ltd. - Acrylonitrile Styrene Acrylate

Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.5 mm		HB	
3.0 mm		HB	

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	80 to 90	°C
Drying Time	2.0 to 3.0	hr
Rear Temperature	180 to 200	°C
Middle Temperature	190 to 210	°C
Front Temperature	210 to 220	°C
Nozzle Temperature	210 to 220	°C
Processing (Melt) Temp	200 to 230	°C
Mold Temperature	40 to 80	°C
Back Pressure	0.490 to 0.981	MPa
Screw Speed	50 to 100	rpm

Injection Notes

Minimum Moisture Content: 0.01%

Notes

¹ Typical properties: these are not to be construed as specifications.

² 23°C

³ 50 mm/min

⁴ 15 mm/min

⁵ Edgewise

⁶ Rate A (50°C/h), Loading 2 (50 N)