

General Information
Product Description

 Description
 Light diffusion
 Weatherability

 Application
 (LED) Lamp cover, Signboard Lighting decoration of electronic device

General

Material Status	• Commercial: Active	
Availability	• Asia Pacific • Europe	• Latin America • North America
Features	• Good Light Diffusion	• Weather Resistant
Uses	• Electrical/Electronic Applications • Lighting Applications	• Lighting Diffusers • Lighting Fixtures
Processing Method	• Injection Molding	

ASTM & ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	33	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.50 to 0.80	%	ASTM D955
Outdoor Suitability	f1		UL 746C
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield, 3.20 mm)	61.8	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	> 100	%	ASTM D638
Flexural Modulus ³ (6.40 mm)	2260	MPa	ASTM D790
Flexural Strength ³ (6.40 mm)	93.2	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	150	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 1.8 MPa, Unannealed, 6.40 mm	126	°C	ASTM D648
RTI Elec	120	°C	UL 746
RTI Imp	105	°C	UL 746
RTI Str	120	°C	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.50 mm	V-2		
1.6 mm	V-2		
2.5 mm	V-2		
3.0 mm	V-2		
Optical	Nominal Value	Unit	Test Method
Transmittance (1000 µm)	57.0	%	JIS K7361

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Lumiplas® LD8550I

LG Chem Ltd. - Polycarbonate

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	100 to 120	°C
Drying Time	3.0 to 5.0	hr
Suggested Max Moisture	0.020	%
Rear Temperature	250 to 270	°C
Middle Temperature	260 to 280	°C
Front Temperature	270 to 290	°C
Nozzle Temperature	270 to 290	°C
Processing (Melt) Temp	280 to 300	°C
Mold Temperature	60 to 100	°C
Back Pressure	0.981 to 3.92	MPa
Screw Speed	40 to 70	rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

² 50 mm/min

³ 15 mm/min