

**General Information**
**Product Description**

LUPLOY PC 1303-15A resin is designed for extrusion and injection molding products. It exhibits an excellent physical property balance of heat resistance, transparency and impact strength.

**Main Characteristics**

- UV stabilizer
- Medium viscosity
- Good mold release

**Applications**

- Appliances
- Outdoor appliances
- Automotive headlamps

**General**

Material Status	• Commercial: Active		
Availability	• Asia Pacific • Europe	• Latin America • North America	
Additive	• UV Stabilizer		
Features	• Good Clarity • Good Heat Resistance	• Good Impact Resistance • Good Mold Release	• Medium Viscosity • UV Stabilized
Uses	• Appliances • Automotive Applications	• Lighting Applications • Outdoor Applications	
Processing Method	• Extrusion	• Injection Molding	

**ASTM & ISO Properties<sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.20	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	15	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Water Absorption (24 hr, 23°C)	0.15	%	ASTM D570
Water Absorption (Equilibrium, 23°C, 50% RH)	0.32	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2340	MPa	ASTM D638
Tensile Strength <sup>2</sup> (Yield, 23°C)	60.0	MPa	ASTM D638
Tensile Strength (Break)	71.0	MPa	ASTM D638
Tensile Elongation (Yield)	6.0	%	ASTM D638
Tensile Elongation (Break)	150	%	ASTM D638
Flexural Modulus	2410	MPa	ASTM D790
Flexural Strength	96.0	MPa	ASTM D790
Taber Abrasion Resistance - Delta Haze <sup>3</sup>	45	%	ASTM D1004
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact <sup>4</sup> (23°C, 3.18 mm)	850	J/m	ASTM D256
Unnotched Izod Impact (23°C)	No Break		ASTM D256
Instrumented Dart Impact <sup>5</sup> (23°C, 3.18 mm, Total Energy)	87.0	J	ASTM D3763

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

# Lupoy® 1303-15A

## LG Chem Ltd. - Polycarbonate

Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	72		
R-Scale	118		
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Annealed, 4.00 mm	143	°C	
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed, 4.00 mm	127	°C	
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Annealed, 4.00 mm	140	°C	
Vicat Softening Temperature	148	°C	ASTM D1525 <sup>6</sup>
Ball Indentation Temperature	> 125	°C	IEC 60598-1
CLTE - Flow (-40 to 82°C)	6.8E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (23°C)	2.0E+17	ohms-cm	ASTM D257
Dielectric Strength	17	kV/mm	ASTM D149
Dielectric Constant (60 Hz)	3.00		ASTM D150
Dissipation Factor (60 Hz)	1.0E-3		ASTM D150
Comparative Tracking Index (2.00 mm)	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.5 mm	HB		
3.0 mm	HB		
Glow Wire Ignition Temperature (2.0 mm, 5.0 sec)	850	°C	IEC 60695-2-13
Oxygen Index	26	%	ASTM D2863
Average Extent of Burning	3	cm	ASTM D635
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.586		ASTM D542
Transmittance	89.0	%	ASTM D1003
Haze	0.700 to 1.50	%	ASTM D1003

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 50 mm/min

<sup>3</sup> CS-10F Wheel, 500 cycles, 1000 g

<sup>4</sup> 0.25 mm Notch Depth

<sup>5</sup> 3.39 m/sec

<sup>6</sup> Rate A (50°C/h), Loading 2 (50 N)