

Ravago Compounds HMP-315 (Roto)

Ravago Manufacturing Americas - High Density Polyethylene

Sunday, November 17, 2019

General Information

Product Description

Key Features:

- 35-mesh powder
- Good moldability
- Excellent long term outdoor weatherability (UV8)
- Balance of toughness and rigidity
- Good low temperature impact
- Improved stiffness
- Excellent environmental stress crack resistance, ESCR
- Compounded for uniform additive dispersion
- Natural as well as standard, custom or special effect colors available
- Stock colors available. See Stock color bulletin
- UL component recognition listing (E141240)
- Also available in pellet form as HM-315

General

Material Status	• Commercial: Active
Availability	• North America
Features	<ul style="list-style-type: none"> • Good Moldability • Good Stiffness • Good Toughness <ul style="list-style-type: none"> • Good Weather Resistance • High ESCR (Stress Crack Resist.) • High Rigidity <ul style="list-style-type: none"> • Low Temperature Impact Resistance
UL File Number	• E141240
Appearance	• Colors Available • Opaque
Forms	• Powder
Processing Method	• Rotational Molding

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.940	g/cm ³	ASTM D792
Apparent (Bulk) Density ²	0.34	g/cm ³	ASTM D1895
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.0	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (ESCR) 100% Igepal, Rotational Molded, F50	500	hr	ASTM D1693B
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, Rotational Molded)	20.7	MPa	ASTM D638
Tensile Elongation (Break, Rotational Molded)	400	%	ASTM D638
Flexural Modulus - Tangent (Rotational Molded)	827	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Impact Strength ³ (-40°C, Rotational Molded)	81	J	ARM
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 0.45 MPa, Unannealed, Rotational Molded	57.0	°C	ASTM D648
Deflection Temperature Under Load 1.8 MPa, Unannealed, Rotational Molded	47.0	°C	ASTM D648

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Ravago Compounds HMP-315 (Roto)

Ravago Manufacturing Americas - High Density Polyethylene

Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.5 mm		HB	
3.0 mm		HB	
Additional Information	Nominal Value	Unit	Test Method
Pourability ²	30.0	sec	ASTM D1895

Notes

¹ Typical properties: these are not to be construed as specifications.

² 35-mesh powder

³ F50